



MICRO-PAVE SUPREME

Premium Grade Asphalt Emulsion Sealer System

Detailed Application Specification

1.0 Objectives:

This specification covers the application of MICRO-PAVE SUPREME Premium Grade Asphalt Emulsion Sealer System for existing, sound asphalt pavements to:

- 1.1 Extend the service life of the asphalt pavement by sealing out:
 - Sun's ultraviolet rays, which result in oxidative decomposition
 - Water and subsequent damage to the sub-base caused by water penetration.
- 1.2 Beautify and enhance the appearance.
- 1.3 Reduce the maintenance costs and extend the service life.
- 1.4 Fill minor surface imperfections and yield an even looking surface.
- 1.5 Provide a limited degree of skid resistance.

2.0 Materials

2.1 MICRO-PAVE SUPREME Premium Grade Asphalt Emulsion Sealer System.

2.1.1 Standards & Specifications: Micro-pave Supreme meets and or exceeds the requirements of the following standards and specifications:

Constants/Property Status	Min.	Max	Method	Micro-pave Supreme	
Weight/Gallon (lb.)	9.0	-	ASTM D244	9.25 Min.	Passes
% Non-Volatile	47	53	ASTM D2929-7849-51		Passes
% Non-Volatile Soluble in 20 carbon disulfide	-		" "	Passes	
% Ash of Non-Volatile	30	40	" "	34-35	Passes
Drying Time, hrs.	-	8	" "	1-4	Passes
Resistance to water			No penetration or loss of adhesion	OK	Passes
Flexibility			No cracking or flaking	OK	Passes
Resistance to impact			No chipping, cracking or flaking	OK	Passes
Well film continuity			Smooth, non-granular, free from coarse particles	OK	Passes
Cured Film color & Viscosity	Black	-	ASTM D562	OK	Passes
Wet track Abrasion	-	35 gm..	ASTM 3910	OK	Passes
Accelerated Weathering			FED. SPEC.- TT-C-555B	OK	Passes

2.1.2 The material shall be homogeneous and show no separation or coagulation components that can not be re-dispersed with moderate stirring.

2.1.3 The material shall be suitable for application and complete coverage, by brush or by approved mechanical methods, to the bituminous surface at a spreading rate of 0.18-0.25 Gal. (based on the amount of MICRO-PAVE SUPREME Concentrated) per square yard in a two (2) coat application system.

2.2 **Sand/Aggregate Specifications:** Sand shall be clean hard and irregular silica sand, free of clay, dust, salt, and organic matter and must meet the following gradation, when tested in accordance with ASTM C136 or Cal tests 202. Sand with AFS rating of 50 to 70, with less than 2% retained on 30 mesh, less than 10% on 140mesh and less than 0.3% retained on 200 mesh screen, is recommended.

U.S. Sieve Size		Percentage Retained	
		Minimum	Maximum
No. 20 or Coarser	(0.850 mm)	0	0

No. 30	(0.600 mm)	0	3
No. 40	(0.425 mm)	7	25
No. 50	(0.300 mm)	15	50
No. 70	(0.212 mm)	20	40
No. 100	(0.150 mm)	3	30
No. 140	(0.106 mm)	0	10
No. 200	(0.075 mm)	0	7
Finer than No. 200		0	0.3

2.3 Water shall be clean and potable, free of harmful soluble salts, within a temperature range of 50-80 degrees °F

2.4 Additive - STAR MICRO-LOCK, is recommended. This specialty additive designed for asphalt emulsion sealcoatings is based on Acrylonitrile/butadiene latex rubber to impart toughness, flexibility and durability. It shall be used per mix design and specification requirements.

2.5 Crack Fillers: Must be certified by the supplier for compatibility with the sealcoating material. Cold pour crack fillers, **STAR STA-FLEX** and the premium grade **STA-FLEX SUPREME**, are recommended by S.T.A.R. Hot pour rubberized crack fillers may also be used.

2.6 Primers:

2.6.1 Oil Spot Primers: Must be certified by the sealcoat manufacturer for compatibility with the sealcoating material. *STAR S.O.S. Primer/Sealer* is recommended.

2.6.2 Pavement Primer: Must be certified by the sealcoat manufacturer for compatibility with the sealcoating material.

2.6.3 Specialty Coatings/Primers may be recommended by the manufacturer for problematic areas, e.g. rust streaks in the pavement, excessive surface contamination with oil, grease, fat etc. *STAR ONE STEP*, pre-mixed with water (in 1:2 volume ratio; STAR MICRO-PAVE SUPREME/water) is recommended for fresh laid asphalt patches and polished aggregates.

3.0 Surface Preparation:

3.1 For new installations, the pavement surface must be cured at least 30 days in hot weather. Check by spreading some water. If the water does not bead and stays in a continuous film, the pavement is suitable for sealcoating.

3.2 Clean the surface thoroughly to remove all foreign debris (dirt, gravel, silt, etc.) using air blowers or pressure washing with water. Embedded dirt and silt shall be removed with steel bristle hand brooms.

3.3 Mud areas shall be thoroughly scraped and pressure washed with clean water.

3.4 Treat all grease and oil spots by scraping off the excess oil and dirt with a wire bristle broom and coat with **STAR OIL SPOT PRIMER SEALER (S.O.S)** in accordance with directions. **STAR ONE STEP** is recommended for the areas contaminated extensively with oil, grease fuel etc.

3.5 Make all necessary repairs, patch soft spots, and fill all cracks and holes in the pavement. All patched areas must be cured before applying **MICRO-PAVE SUPREME**.

3.6 On excessively weathered surfaces or areas that cleaning operation leave a film of dust, a tack coat shall be applied. The tack coat shall consist of one (1) part of asphalt emulsion (SS-1-H) mixed with four (4) parts of water by volume or one (1) part of MICRO-PAVE SUPREME mixed with two (2) parts of clean water. Apply the mixture at a rate of

0.05 to 0.10 Gal./Sq. yard. Allow the primer coat to dry thoroughly prior to sealcoating with **MICRO-PAVE SUPREME**.

4.0 Recommended Mix Designs and Application Specifications:

4.1 Mix Designs: MICRO-PAVE SUPREME as supplied is in a highly concentrated form and it has to be mixed with water, mineral aggregates and specialty additives, for use as a sealcoating system. The use of an additive is frequently recommended.

Standard Mix Design:

MICRO-PAVE SUPREME	-100	Gals.
Water	-10 to 20	Gals.
Sand or Aggregates	-300 to 500	Lbs.

4.2 Application Specifications:

All application rates are expressed as gallons of the above mixture used/square yard of the pavement.

Typical sealcoating applications require two (2) coats of the above mixture. Each application of the mixture shall be at a rate of 0.14 to 0.22 gallons per square yard per coat, i.e. 0.28-0.44 gallon per square yard for two (2) coats. The coverage rate and the material usage will vary according to pavement porosity, weather conditions and traffic requirements. The mix designs shall be modified to accommodate such conditions for an optimum performance.

4.2.1 LOW & MEDIUM TRAFFIC areas: parking lot, home driveways, airfields, bridge decks etc. Apply two (2) coats of the ready to use material. The suggested composition is as follows:

MICRO-PAVE SUPREME	-100	Gals.
Water	-15	Gals.
Sand	-500	Lbs.

Coverage rate: Approx. 0.24 Gal./Square Yard for two (2) coats.

4.2.2 HIGH TRAFFIC Areas Service stations, high traffic parking lots (exit and entrance). Apply three (3) sand slurry. The suggested composition is as follows:

MICRO-PAVE SUPREME	-100	Gals.
Water	-20	Gals.
Sand	-300	Lbs.

Coverage rate: Approx. 0.35 Gal./Square yard for three (3) coats.

4.3 For aged pavements: For excessively oxidized pavements, a total of three (3) coat system is recommended, the very first coat being a primer coat followed by a standard two (2) coat MICRO-PAVE SUPREME sand slurry system.

4.4 Sand Slurry Preparation

-Add the required amount of water to MICRO-PAVE SUPREME in the mixing tank and mix thoroughly.

-Keep the mixer running at a moderate rate.

-Add the sand in a steady stream of about one 100 lbs. bag per minute. While adding sand be sure of firm footing and never place hands and arms in the agitating mixer.

-After adding all the sand, close the lid of the mixing tank and raise the speed of the mixer to "high" setting.

-Mix for 10 minutes to allow the contents of the tank to mix thoroughly and break any sand clumps

-Reduce the agitator speed to moderate setting and keep running. If the mixer is shut off during transport to the job site, it must be restarted and contents mixed for at least 10 minutes before the application begins. Keep it running during the entire application period.

5.0 Application of Material

5.1 The material shall be mixed according to the specifications detailed in Section 4.2. Quantities of the material will vary according to porosity and texture of the pavement. The mix designs (i.e. **MICRO-PAVE SUPREME** and other ingredients) expressed in sections 4.2 are for guidelines only.

5.2 MICRO-PAVE SUPREME must be applied when ambient and pavement temperatures are above 60 °F. Good drying conditions are required during the subsequent 24 hrs. but never below 60 °F. Nighttime application is not recommended.

-The first coat, MICRO-PAVE SUPREME sand slurry, shall be uniformly applied over the entire surface. If the surface temperature is more than 90 degrees °F, pre-dampen with a light mist. Avoid puddles. There should be no free standing water.

-Allow the first coat to dry sufficiently to take light traffic without scuffing. Under ideal drying conditions, it will take about 1-2 hours. Ideal drying conditions are temperatures of 70-80 °F, sunlight, relative humidity 50% or lower and movement of air. Lower temperatures, high humidity, clouds or shade and lack of air movement retard the cure.

-If the specification calls for a second coat, apply it perpendicular to the previous coat, if practical.

-The completed application shall be allowed to cure at least for 24 hours and tested for traffic-ability prior to opening for regular use.

6.0 Method of Applications

6.1 Squeegee/Brush (Hand Application) method:

The agitator in the sealer tank should be kept on to keep the material in suspension at all times. The machine should be equipped with a fog bar to be used for pre-dampening if the pavement temperature exceeds to degrees °F.

Coat the edges first. Pour a continuous ribbon of the MICRO-PAVE SUPREME mix along the pavement edge 6-12 inches from curbing.

Draw MICRO-PAVE SUPREME mix away from the pavement edge by pulling a squeegee or brush perpendicular through the ribbon of material at a slight angle. Walk

parallel to the pavement edge. Repeat the process in reverse direction pulling the excess material toward the center of the pavement. For best results, use a squeegee followed by a brush. Pour more MICRO-PAVE SUPREME mix to maintain a working ribbon of material and continue across the pavement until it is completely covered.

6.2 Machine application:

When applying by machine, seal the edges of the pavement by hand. The machine should then be used to apply MICRO-PAVE SUPREME mix to remaining area. A self-propelled machine that squeegees and brushes the sealer into the pores of the pavement is recommended.

Spray application should deposit the material according to the coverage rates recommended for the specified job.

7.0 Striping

If striping is required, use **STAR-BRITE Latex Traffic Paint (TT-P-1952b) or STAR BRITE PLUS, fast drying-100% Acrylic Traffic Paint**. Allow the seal coat to dry at least 24 hours before striping. Refer to the Technical Data Sheet for details.

8.0 Precautions:

8.1 MICRO-PAVE SUPREME must be protected from freezing. Do not store at temperatures below 32 degrees °F.

8.3 Drying is retarded by excessive moisture in air or ground. Examples: rain, fog, prolonged humidity and seasonal extreme (early Spring - late Fall). Under such conditions, the use of **MICRO-LOCK** is recommended to obtain optimum and uniform drying.

8.4 Follow the recommended coverage rates. If MICRO-PAVE SUPREME is applied too heavy, the surface will dry and restrict the water evaporation from the rest of the film, slowing down the complete drying process.

8.5 Keep out of the reach of children.

8.6 Refer to the Material Safety Data Sheet (M.S.D.S.) for all relevant details.

Disclaimer:

These specifications report accurate and reliable information to the best of our knowledge, however, no expressed or implied warranties are extended by the manufacturers due to that the conditions of use and workmanship are beyond the controls of the manufacturer. S.T.A.R., Inc. assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.

Edition: March, 2006

